

## Type JP02

### Tied Rubber Bellows.

Now Available With Precision Fit Flexible Lagging Jackets To Suit JP02.

## Specification

Tied E.P.D.M. rubber bellows with nylon reinforced body and steel reinforced collar. Fitted with zinc plated carbon steel swivel flanges. Drilled to BS. 4504 NP16.

## Application

Stourflex untied rubber bellows are designed to accommodate misalignment and both axial and lateral movement. They are also used to reduce noise and vibration from pumps and reciprocating machinery.

Maximum test pressure = 1.5 x working pressure or 1.5 x flange rating, whichever the lower.

### Maximum Pressure & Temperatures

Up to 90°C	6 Bar
Up to 82°C	10 Bar
Up to 70°C	16 Bar
Chilled	16 Bar



## Lagging

Stourflex are now able to offer a tailor made flexible lagging jacket to help reduce heat losses on LTHW systems and heat gains & condensation on CHW systems. Please ask for more information.

Part number	N.B. (mm)	Installed Length (mm)	Tie Bars	Lateral (mm)
JP02-25-16	25	130	2	13
JP02-32-16	32	130	2	13
JP02-40-16	40	130	2	13
JP02-50-16	50	130	2	13
JP02-65-16	65	130	2	13
JP02-80-16	80	130	2	13
JP02-100-16	100	130	2	13
JP02-125-16	125	130	2	13
JP02-150-16	150	130	2	13
JP02-200-16	200	130	2	13
JP02-250-16	250	130	2	13
JP02-300-16	300	130	4	13

Supplied length may vary. Tolerance +/-5%

For sizes above 300mm N.B. please refer to the JP04 tied rubber bellows.

Where vacuum conditions or pressures and temperatures above those stated exist, please check with us the suitability of and effects on service life of Stourflex products.

Alternative flange drillings and materials are available on request.

Stourflex products should be installed in accordance with our fitting instructions.

Stourflex rubber bellows should be periodically inspected and replaced if any deterioration is evident.


## Installation, Operation and Maintenance Instructions For Rubber Bellows

**Storage** Rubber bellows should be stored in a cool, dark, clean area and be protected from damage caused by other items of plant and equipment.







**Inspection** Rubber bellows should be inspected for internal and external damage prior to installation. The rubber bellows sealing surface should be clean and free from any debris that would prevent a seal or cause damage to the bellows in service.

**Selection** The Stourflex range of rubber bellows are supplied at varying lengths. The movements stated in the datasheet can only be achieved when the given installation lengths are adhered to.





Check that the correct rubber bellows have been selected for the operating conditions that exist. Temperature, pressure and movement should all be confirmed, as the wrong selection may result in failure of the system. Also check whether vacuum conditions exist and if so whether a vacuum support ring is required and has been fitted.





**Installation** Rubber bellows should be installed at their neutral (supplied) length. Confirm that the gap left between the mating flanges in the pipework corresponds exactly with the neutral (supplied) length of the rubber bellows. Pipework should be true and straight. Any adjustments should be made to the pipework before the rubber bellows are fitted. See appropriate Stourflex data sheets for the installation length of the rubber bellows being installed.



Only the correct mating flanges should be used. They should be the same size and drilling and have a similar sealing face as that of the rubber bellows. They must be clean and free from any debris, sharp edges etc. to prevent damage occurring to the sealing face of the bellows. For mating flanges with a different sealing face diameter a composite gasket should be used to prevent any sharp edges cutting into the rubber sealing face.





Flange bolts must not be over tightened, bolts should be tightened gradually and evenly and in a crosswise manner. Bolts should be positioned so that the bolt head is nearest the bellows to prevent the bolt damaging the bellow in service. Tightness of bolts should be checked approximately seven days after installation.



## Installation, Operation and Maintenance Instructions For Rubber Bellows Continued

### Installation Continued

When tied rubber bellows are being used they must be installed at their neutral (supplied) length. Recheck installation length and movement capabilities of the bellows being installed. Ensure that the steel washers and the rubber top hat washers have been correctly fitted. Tie bar assemblies should be uniformly tightened and bolts rechecked after approximately seven days.





### Pressure Test



If a hydraulic pressure test is to be carried out on a system containing rubber bellows, ensure that the anchors are correctly fitting before the test is carried out. Also ensure that the test pressure (usually 1.5 x working) does not exceed the maximum test pressure of the rubber bellows.

### Anchoring

Rubber bellows must be anchored to ensure their correct performance. Tied rubber bellows should be selected for the sizes above 80mm and where pressures exceed 3bar.



Rubber bellows will exert a pressure thrust in service and must be anchored to protect adjacent pipework and equipment. Rubber bellows will extend under pressure and must be anchored to prevent this happening.



### Maintenance

When properly installed and used at their correct operating temperature and pressure, rubber bellows will give many years of trouble free service. However rubber bellows should be inspected periodically for signs of deterioration. If insulation is to be used, this should be removable to allow inspection to be carried out. Flange bolts should be checked and re-tightened if required. Rubber bellows should not be painted as this may reduce service life. If fine hair cracks become evident in bellows membrane this is a sign that the bellows is nearing the end of its service life and should be replaced at the next convenient opportunity. A rubber bellows is an important part of any heating or chilled water system and consideration should be given to keeping a quantity of spares that would prevent a long term shutdown of the system.

### **WARNING**

Please note using Stourflex rubber bellows over their stated maximum temperature and or pressure can cause premature ageing of the rubber body and result in burst failure.

We recommend Stourflex rubber bellows are inspected regularly as part of a routine maintenance procedure, any cracking/blistering of the rubber body, weeping or noticeable hardening of the rubber body then the bellows must be isolated and replaced immediately!

Any queries please contact Stourflex to discuss.